



Innovative Polyester *Films*
Electronics



Delivering flexible substrates for
advanced electronics applications

Melinex® Mylar®

Mylar® and Melinex® PET films

- excellent electrical properties
- ease of handleability
- superb optical clarity
- long flex life
- embossable
- printable
- pretreatments for enhanced adhesion

FILM TYPE	THICKNESS (MICRON)	SURFACE PRETREAT	TYPICAL APPLICATIONS
Standard Films, for use where shrinkage is not critical or where film is stabilised in-house			
Mylar® A	12-500	None	Strong, durable, hazy film with excellent handleability for MTS and FPC applications.
Melinex® OD	125-250	None	Optically clear for MTS graphics.
Melinex® 339	50-250	2-side adhesion	White film with high opacity and excellent printability.
Melinex® 506	75-250	2-side adhesion	Optically clear with excellent printability and ink adhesion.
Melinex® 715	125-250	1-side adhesion	Optically clear with excellent adhesion to UV inks and lacquers.
Melinex® 726	125-175	2-side adhesion	Optically clear with superb adhesion to circuitry inks for FPC applications.
Melinex® TCH11	50-125	1-side index match	Optically clear, low bloom with anti-iridescence for touch screen applications.
Films with lower shrinkage, for improved performance over standard films			
Mylar® ADS	50-125	None	Lower shrinkage version of Mylar® A suitable for FPC and MTS circuitry.
Fully heat stabilised optically clear films with very low shrinkage, where ultimate PET film performance is required			
Melinex® ST504	125-175	1-side adhesion	Low bloom with adhesion pre-treat developed for ITO sputtering and other deposition processes.
Melinex® ST506	100-250	2-side adhesion	Low bloom with excellent printability and ink adhesion suitable for MTS graphics and circuitry applications.
Melinex® ST510	125-250	1-side adhesion 1-side index match	Low bloom with anti-iridescence and printable surfaces for touch screen.
Melinex® ST726	125-175	2-side adhesion	Optically clear with superb adhesion to circuitry inks for FPC applications.
Melinex® STCH11	50-125	1-side index match	Low bloom with anti-iridescence for touch screen.
Melinex® STCH12	50-125	2-side index match	Low bloom with anti-iridescence for touch screen on both sides.
Other development PET film grades are available to meet specific application needs. Please enquire for further details.			



Teonex®

Teonex® PEN Films

- superior thermal and hydrolytic stability
- improved barrier properties
- superb optical clarity
- suitable for mild soldering
- higher modulus to density ratio
- more temperature - resistant embossing
- very low shrinkage (heat stabilised)

FILM TYPE	THICKNESS (MICRON)	SURFACE PRETREAT	TYPICAL APPLICATIONS
PolyEthylene Naphthalate (PEN) Films			
Teonex® Q51	12-250	None	Standard grade PEN film with excellent handleability.
Teonex® Q83	25-125	None	Heat stabilised PEN film with a very low shrinkage up to 230°C. Designed for FPC applications requiring soldering.
Teonex® Q51DW	25	2-side adhesion	Standard grade PEN film with enhanced adhesion to many solvent based systems and excellent handleability.
Teonex® Q65H	50-125	1-side adhesion	Optically clear PEN film with adhesion pretreat for sputtering in flexible electronics applications.
Teonex® Q65HA	50-125	1-side adhesion	Optically clear heat stabilised PEN with very low shrinkage up to 230°C.
Optfine® PQDA5	50-125	1-side planarised, 1-side hard coat	Smooth, defect free surface for advanced electronics applications.

Other development PEN film grades are available to meet specific application needs. Please enquire for further details.

Flexible Printed Circuits (FPC) Flat Flexible Cables (FFC)

- films for copper laminates and adhesive coverlays
- applications in automobile wiring, appliances, RFID tags, smart card lead frames and antennae

Membrane Touch Switch (MTS)

- films for circuit, graphics and spacer layers
- applications in automotive seat sensors, industrial and domestic equipment, keyboards, mobile phones

Flexible Electronics

- films for ITO sputtering and hard coating
- applications in touch screens, electroluminescent lamps, flexible displays





This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont Teijin Films makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see 'DuPont Teijin Films Medical Caution Statement', H-50102-1-DTF.

Melinex® and Mylar® are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin Films Solutions and licensed to DuPont Teijin Films U.S. Limited Partnership.

Date of Last Revision: 22 February 2017

United Kingdom

DuPont Teijin Films U.K. Ltd
The Wilton Centre
Redcar
TS10 4RF
Tel +44 (0) 1642 572000
Fax +44 (0) 1642 572128

Continental Europe

DuPont Teijin Films Luxembourg S.A.
BP-1681
L-1016
Luxembourg
Tel +352 2616 4004
Fax +352 2616 5000

United States

DuPont Teijin Films U.S.
Limited Partnership
3600 Discovery Drive
Chester, VA 23860 USA
Tel +1 800 635-4639
Fax +1 804 530-9862

Asia Pacific

DuPont Teijin Films China Limited
26/F, Tower 6, The Gateway
9 Canton Road, Tsimshatsui
Kowloon, Hong Kong
Tel: +852 2734 5345
Fax: +852 2369 8151